

flexlink 1100 r+

article no.: 3240

Version 03/ 28.09.2011
Supersedes Version 02/ 17.03.2009

flexlink 1100 r+ is a high performance adhesive tape system with a syntactic, specially modified acrylate foam.

This tape is specially designed for applications on smooth or textured, flat or uneven surfaces.

Because of the thickness of the adhesive, the product offers excellent gap filling properties. It is good to bond a wide variety of materials such as plastics, metals, glass, ceramics.

The flexlink 1100 r+ provides good levels of tack, for sub assembly and production processes, with a bond strength that increases over time.

Tape Construction



HDPE film, blue,
both sides siliconised
thickness: 125 µm

Specially modified acrylate,
white
thickness: 1100 µm

Tape Thickness

approx. 1,1 mm excl. liner

Adhesion [N/25mm]

In accordance to AFERA 5001

steel	34	PMMA	29
aluminium	30	PVC	28
glass	28	PP	22
		PE	13

Cohesion [N/625mm²]

In accordance to AFERA 5012

20° C	45	70° C	10
-------	----	-------	----

Temperature Resistance

- 40°C to +120°C, short term even up to +160°C

Storage. This product should be stored at ambient temperatures of around 20°C, avoiding wide temperature fluctuations and direct sunlight. The storage environment should have a relative humidity of approx. 50%. In ideal storage conditions, the shelf life of this material will be approx. 12 months from the delivery date. Within this 12 month period, when stored correctly, there should be no deterioration of the products published performance specification.

Product use. All statements, technical info contained herein are based on lab testing, we believe to be reliable. In reality, many factors beyond our control can affect and influence the use and performance of our products on any particular application. Since these factors are uniquely within the users knowledge and control, it is essential that the user evaluate the product to determine its suitability for purpose. Biolink will not be liable for any loss or damage arising, whether direct or indirect, special, incidental or consequential.

All data above mentioned and technical information given above are typical values, gained from tests we believe to be reliable. Please ensure before using. Our product that it is suitable for the material for intended application. For technical assistance please call our product specialists. The data and statements are intended as a source of information, are given without guarantee and do not constitute a warranty. They can vary according to the application conditions. All materials described herein are subject to our conditions of sale, a copy is available on request.