

foamlink 11032 h+


article no.: 4177

Version 02/28.09.2011
 Supersedes Version 01/04.08.2009

foamlink 11032 h+ is a double coated foam tape with a modified acrylate adhesive.

The closed cell, Polyolefin-foam carrier provides good conformability and is therefore ideal for use on both smooth and uneven or textured surfaces. The adhesive is a modified acrylic adhesive, that provides both good tack and good permanent bonding characteristics. It should be used for glass, metals and most plastics. The combination of adhesive and foam carrier is good for die cutting and converting.

Tape Construction



Siliconpaper, yellow,
 both sides siliconized,
 weight: 90 g/m²

closed side:
 Modified acrylate,
 coat weight: 70 g/m²

Polyolefin-foam, white
 thickness: 1,0 mm

open side:
 Modified acrylate,
 coat weight: 70 g/m²

Tape Thickness

approx. 1,1 mm excl. liner

Adhesion [N/25mm]

In accordance to AFERA 5001

steel*	27	PMMA*	25
aluminium*	25	PVC*	26
glass*	26	PP*	25
		PE	15

* Indication of foam tear

Cohesion [N/625mm²]

In accordance to AFERA 5012

20° C	45	70° C	15
--------------	-----------	--------------	-----------

Temperature Resistance

- 40°C to +70°C, short term even up to +90°C

Storage. This product should be stored at ambient temperatures of around 20°C, avoiding wide temperature fluctuations and direct sunlight. The storage environment should have a relative humidity of approx. 50%. In ideal storage conditions, the shelf life of this material will be approx. 12 months from the delivery date. Within this 12 month period, when stored correctly, there should be no deterioration of the products published performance specification.

Product use. All statements, technical info contained herein are based on lab testing, we believe to be reliable. In reality, many factors beyond our control can affect and influence the use and performance of our products on any particular application. Since these factors are uniquely within the users knowledge and control, it is essential that the user evaluate the product to determine its suitability for purpose. Biolink will not be liable for any loss or damage arising, whether direct or indirect, special, incidental or consequential.

All data above mentioned and technical information given above are typical values, gained from tests we believe to be reliable. Please ensure before using. Our product that it is suitable for the material for intended application. For technical assistance please call our product specialists. The data and statements are intended as a source of information, are given without guarantee and do not constitute a warranty. They can vary according to the application conditions. All materials described herein are subject to our conditions of sale, a copy is available on request.